



MD-500GR (Green) UV CURABLE DIELECTRIC POLYMER THICK FILM INK

MD-500GR is a UV Curable Screen Printable Dielectric Coating designed to be used as an insulator for printed circuitry.

The MD-500GR provide excellent levels of adhesion making it an ideal protective and insulating coating suited for use as dielectric layers, crossovers and tail coating for membrane switch applications.

The MD-500GR adheres well to both polycarbonate and polyester fim, the polyester film should be pretreated to provide the best adhesion.

The characteristics of the MD-500GR provide excellent flexibility and superior levels of abrasion resistance. The excellent adhesion properties of the dielectric enable the MD-500GR to pass crosshatch tape tests.

Appearance Colour Viscosity (Brookfield DV-11 SP14 20rpm, 25°C) Density Flash Point Shelf Life Dielectric Strength (ASTM D-149 Method A)	Transparent Green 11,000 ± 500 cps 1.28 g/ml 156°C 6 mths in unopened container 1500V AC @ 25µm (Cured)
--	---

Printing Screen Type Squeegee Type Emulsion Dilution Curing Cycle @ 25µm Storage Handling Protection	Suitable for Manual, Semi-Automatic or High Process's Monofilament Polyester 61-120 T/HD Polyurethane 60 Durometer Diazo Sensitised Direct Photo Film Not Required (Ready for Use) Two UV lamps of 120 watt/cm at belt speed of 18m/min or two UV lamps of 80 watt/cm at a belt speed of 12m/min. Thickness greater than 25µm, lower speeds and higher lamp intensities will be required Store product at 2-25°C (shelf life longer at lower storage temperatures) Ensure the MD-500GR is at room temperature before use Protect against exposure to UV sources such as daylight and flourescent lighting (care should be taken to avoid curing on the screen)
--	---

Safety & Handling:

The following precautions should be exercised when handling:

Avoid prolonged contact with skin. If contact with skin occurs, wash immediately with soap and water

Use with adequate ventilation, avoid prolonged breathing of vapour.

Dangerous if swallowed - DO NOT CONSUME

The performance characteristics are influenced and affected by printing technique, nature of substrate, curing time, curing temperature and type of drying equipment.

Before adopting our products for commercial use, the user assumes responsibility for determining fitness of use in their particular application and process. Memcon makes no warranties and assumes no liability in connection with any use of this information.

MEMCON (Asia) Limited
 Level 7 Parkview Centre
 7 Lau Li Street Causeway Bay Hong Kong
 T +852 3741 1411 F +852 3747 8980
 www.memcon.asia sales@memcon.asia

MEMCON Limited
 Compass House Vision Park Chivers Way HISTON
 Cambridge CB24 9AD United Kingdom
 T +44 1223 257724 F +44 1223 257800
 www.memcon.eu sales@memcon.eu

MEMCON North America
 3786 Stadium Drive Bridgman
 Michigan 49106 USA
 T +1 269 466 5632 F +1 269 466 6034
 www.memcon.net sales@memcon.net